

Abstract

Non-stick coatings for use on a flexible substrate include a fluoropolymer, an acrylic polymer, and a polyol and/or diol. The ratio of acrylic polymer to polyol and/or diol is between about 90:10 and about 10:90 by weight, preferably about 50:50. The ratio of acrylic polymer and polyol or diol to fluoropolymer is preferably about 100:60 by weight.

5